

EPOMAX-MT

Three-component, high-strength, pourable epoxy grout

Description

EPOMAX-MT is a 3-component, pourable, high-strength, non-shrink grout, based on a two-component solvent-free epoxy resin (Parts A & B) and a special selected quartz sand (Part C). It provides:

- Very good fluidity
- High initial and final strength
- Excellent bond strength to steel and concrete
- Resistance to impact and vibration
- Chemical resistance
- Waterproofing

Certified according to EN 1504-3 and EN 1504-6 as a mortar for concrete repairs and as an anchoring product for reinforcing steel bars respectively. CE marked.

Fields of application

EPOMAX-MT is used in a wide range of grouting applications where high strength is required, such as:

- Anchor bolts
- Machine bedding
- Bridge bearings
- Stanchions

It can also be used as a pourable mortar for repairs in damaged concrete elements.

Technical data

Base (A, B):	2-component epoxy resin
Base (C):	quartz sand
Mixing proportion (A:B:C):	3:1:16 by weight
Form:	flowable mortar
Color (A+B+C):	light grey
Density (A+B+C):	1.9 kg/l
Pot life:	~ 40 min at +23°C
Minimum hardening temperature:	+8°C
Walkability:	after 16 h at +23°C
Recoat time:	within 24 h at +23°C

Final strength:	after 7 days at +23°C
Compressive strength: (EN 12190)	> 90 N/mm ²
Flexural strength: (EN 12190)	>30 N/mm ²
Chloride content: (EN 1015-17)	0.00%
Adhesion strength: (EN 1542)	> 3 N/mm ² (concrete failure)
Adhesion after 50 freeze thaw cycles: (EN 13687-2)	> 3 N/mm ² (concrete failure)
Capillary water absorption: (EN 13057)	< 0.1 kg·m ⁻² ·h ^{-0.5}
Abrasion resistance: (BCA method – EN 13892-4)	AR 0.5
Pull out strength (EN 1881):	Displacement ≤ 0.6 mm at load of 75 kN
Durability under tensile load: (EN 1544)	Displacement ≤ 0.6 mm after continuous load of 50 kN after 3 months
Glass transition temperature (EN 12614)	≥ 45°C

Cleaning of tools:

Tools should be cleaned with SM-27 solvent immediately after use.

Directions for use

1. Substrate

The surface should be:

- Dry and stable.
- Free of materials that prevent adhesion, e.g. dust, loose particles, grease, formwork oils, existing surface treatment with concrete curing agents, old coatings, etc.

Depending on the nature of the substrate, it should be prepared by brushing, grinding, sandblasting, water blasting, shot blasting, etc. Following this, the surface should be cleaned from dust by air blasting.

EPOMAX-MT

2. Formwork

The formwork used for casting the grout must be leakproof and arranged to allow gravity flow to fill completely the void to be grouted. Formwork should be coated with formwork release agent such as SPLIT-2000, to allow easy removal of forms.

3. Mixing of the components

Components A (resin) B (hardener) and C (sand) are packaged in separate containers, having the correct predetermined mixing ratio by weight.

First, stir component A vigorously. Then, add the entire contents of component B to component A.

Mixing of the 2 components should take place for about 1-2 minutes, using a low-speed mixer (300 rpm). It is important to stir thoroughly the mixture near the sides and bottom of the container, to achieve uniform dispersion of the hardener.

Place the mixed A and B components into a larger clean mixing bucket and continue mixing while adding component C slowly to keep air entrapment at a minimum. The mixing is being done by using a low-speed mixer (300 rpm) until an even distribution of the aggregates throughout the mix has been achieved (approx. for 3-5 minutes).

4. Application – Consumption

Mixed EPOMAX-MT should be poured into the formwork from one side continuously, to avoid air entrapment. For bolt anchoring fill first at least half the volume of the performed holes before placing the bolt in the grout.

Maximum layer thickness is 5 cm. If necessary, apply a successive layer within 24 hours from the application of the first layer.

Consumption

Approx. 1.9 kg/l.

Packaging

EPOMAX-MT is supplied in container (A+B+C) of 25 kg.

Shelf life – Storage

12 months from date of production if stored in original sealed packaging, in areas protected from humidity and frost. The recommended storage temperature is between +5°C and +35°C.

Remarks

- The workability of epoxy materials is affected by their temperature. The ideal temperature of application is between +15°C and +25°C so that the product will be easy to use and cure as prescribed. Room temperature below +15°C will extend the curing time while temperature above +30°C will accelerate it. It is recommended to mildly preheat the product during winter, and store the product in a cool room before application during summer.
- Bonding between successive layers may be severely affected by moisture or dirt.
- Epoxy layers should be protected from moisture for 4-6 hours after application. Moisture may whiten the surface or/and make it sticky. It may also disturb hardening. Faded or sticky layers in parts of the surface should be removed by grinding or milling and laid again.
- In case recoat time is longer than expected or in case old floors are to be overlaid again, the surface should be thoroughly cleaned and ground before application of the new layer.
- After hardening, EPOMAX-MT is totally safe for health.
- Please consult the directions for safe use and precautions written on the packaging before use.

EPOMAX-MT


ISOMAT S.A. 17 th km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag Athanasios, Greece 13
EN 1504-3 Concrete repair product, PC (Polymer Concrete) DoP No.: EPOMAX-MT/1205-03 Compressive strength: class R2 Chloride ion content: $\leq 0,05\%$ Adhesive Bond: $\geq 0,8$ MPa Thermal compatibility part 1: $\geq 0,8$ MPa Capillary absorption: $\leq 0,5 \text{ kg} \cdot \text{m}^{-2} \cdot \text{h}^{-0,5}$ Dangerous substances: comply with 5.4 Reaction to fire: NPD


2032 ISOMAT S.A. 17 th km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag. Athanasios, Greece 22 2032-CPR-10.11
EN 1504-6 Anchoring of reinforcing steel bar DoP No.: EPOMAX-MT /1309 Pull-out strength: displacement $\leq 0,6$ mm at load of 75 kN Chloride ion content: $\leq 0,05 \%$ Glass Transition temperature: $\geq 45^{\circ}\text{C}$ Reaction to fire: NPD Creep under tensile load: displacement $\leq 0,6$ mm after continuous loading of 50 kN for 3 months Dangerous substances: comply with 5.3

ISOMAT S.A.
BUILDING CHEMICALS, MORTARS & PAINTS
HEADQUARTERS – THESSALONIKI, GREECE
17th km Thessaloniki – Ag. Athanasios Road
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece
T +30 2310 576000
www.isomat.eu e-mail: support@isomat.eu