




**MONOSI SYSKEVASIA S.A.**  
 EPS PRODUCTS MANUFACTURER  
 70th Km. N.R. ATHENS-LAMIA, 34100, AVLIDA, GREECE  
 Business Registration Number : 46148222000  
 T : 2262089840 , F : 2262089852 , E : info@monosieps.gr



## DECLARATION OF PERFORMANCE

No : W120/27.01.2025 - CPR (EU) 305/2011



Unique identification code of the product type : **airpop bianco EPS I20**

EPS-EN13163-T1-L2-W2-S2-P3-DS(N)2-DS(70,90)1-BS170-CS(10)120-TR200-SS85-GM2244-MU30-WL(T)1,5-WL(P)0,10

External Thermal Insulation Applications For Buildings - Thermal Insulation Applications For Buildings

Manufacturer : **MONOSI-SYSKEVASIA S.A.**

System of AVCP : 3

Notified Laboratory : IMBiGS No 1454

The above designated product is produced in accordance with the standard :

**EN 13163:2012+A2:2016** "Thermal insulation products for buildings - Factory made expanded polystyrene (EPS) products - Specification" and fulfills the requirements for ETICS according to : **EAD 040083-00-0404** ( based on Confirmation **347633 THERM / DQS** ).

Essential characteristics		Performance									Standard
Thermal conductivity $\lambda_D$		0,034 W/mK									EN12667
Thermal resistance $R_D$	Thickness	30mm	40mm	50mm	60mm	70mm	80mm	90mm	100mm	110mm	
	m <sup>2</sup> k/W	0,85	1,15	1,45	1,75	2,05	2,35	2,60	2,90	3,20	
	Thickness	120mm	130mm	140mm	150mm	160mm	170mm	180mm	190mm	200mm	
	m <sup>2</sup> k/W	3,50	3,80	4,10	4,40	4,70	5,00	5,25	5,55	5,85	
Thickness tolerances (d)		±1mm									EN823
Length tolerances (l)		±2mm									EN822
Width tolerances (b)		±2mm									EN822
Squareness tolerances on length and width (S <sub>b</sub> )		±2mm/m									EN824
Maximum deviation from Flatness (S <sub>max</sub> )		3mm									EN825
Reaction to fire of the product as placed on the market		Euroclass E									EN13501-1
Durability of reaction to fire of the product as placed on the market against ageing/degradation		not changed with time									EN13163
Durability of thermal resistance and thermal conductivity against ageing/degradation		not changed with time									EN13163
Dimensional stability under constant normal laboratory conditions (23°C,50%R.H.),(Δε <sub>l</sub> / Δε <sub>b</sub> )		±0,2%									EN1603
Dimensional stability under specified temperature and humidity conditions (48h,70°C,90%R.H.),(Δε <sub>l</sub> ,Δε <sub>b</sub> ,Δε <sub>d</sub> )		≤1%									EN1604
Bending strength (σ <sub>b</sub> )		≥170 kPa									EN12089
Compressive stress at 10% deformation (σ <sub>10</sub> )		≥120 kPa									EN826
Tensile strength perpendicular to faces (σ <sub>mt</sub> )		≥200 kPa									EN1607
Short-term water absorption by partial immersion (W <sub>sp</sub> )		<1 kg/m <sup>2</sup>									EN29767
Long-term water absorption by partial immersion (W <sub>lp</sub> )		≤0,1 kg/m <sup>2</sup>									EN16535
Long-term water absorption by total immersion (W <sub>lt</sub> )		≤1,5%									EN16535
Shear strength (τ)		≥85 kPa									EN13163
Shear modulus (G)		≥2244 kPa									EN13163
Water vapour diffusion resistance factor (μ)		30-70 (1)									EN13163
Water vapour permeability (δ)		0,009-0,020 mg/(Pahm)									EN13163

EPS blocks intended to be used in an **ETICS** application are aged for at least **28** days before cut into boards.

The conformity of the product is verified by the appropriate technical documentation .

The performance of the product identified above is in conformity with the set of declared performances. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

Member of AUSTROTHERM GROUP



**MONOSI SYSKEVASIA S.A.**  
 DISTINCTIVE TITLE: STYROPAN S.A.  
 EPS PRODUCTS MANUFACTURER  
 70th km ATHENS - LAMIA, 34100, AVLIDA  
 P.O. BOX 58, 32009 SCHIMATARI, GREECE  
 VAT No: EL094463983 - REG.No: 046148222000  
 Tel: (+30) 22620 89840 - Fax: (+30) 22620 89852  
 E-mail: info@monosieps.gr

January 27, 2025

Date of issue

Ilias Stousidis  
 General Manager

Name / Position

Sign/Signature